## **Levelling Tester**




The Levelling Tester is designed to determine the relative levelling of liquid coating materials before curing in the laboratory. (Coating materials have to eliminate surface defect during drying). It complies with ASTM D2801-1994 (T01-700133) and NYPC (T01-700134)

It is made of stainless steel with a straight scraper fitted with 5 pairs of notches of increasing depth from  $100 \sim 1000 \mu m$  (or  $250 \sim 4000 \mu m$ ).

Once the drawdown has been made on a horizontal, firm surface, leave the coating to cure. Once the coating is dry, identify the thickness at which the pair of film stripes merge.

Product Code	Coating Thickness	Dimensions	Weight
T01-700133	100-200-300-500-1,000µm	120×20×20mm	0.3 Kg
T01-700134	10-20-40-80-160 mils	120×20×20mm	0.3 Kg





Ascott Analytical Equipment Limited

6-8 Gerard, Lichfield Road Industrial Estate, Tamworth, Staffordshire, B79 7UW, Great Britain T +44 (0) 1827 318040 F +44 (0) 1827 318049 E info@ascottshop.com W www.ascottshop.com

## Testing climate resistance to the limit